

# Conduct-O-Bond

## ECS2000

### Technical Data Sheet Conduct-o-Bond ECS2000 Electrically Conductive Adhesive

**Conduct-o-Bond 2000** is a one part, silicone base, electrically conductive adhesive containing micron sized Nickel Coated Graphite particles as the conducting and shielding media. **ECS Conduct-o-Bond 2000** is a room temperature vulcanizing (RTV) and sealing material that cures in the presence of atmospheric moisture. This adhesive is specially formulated with a high quality non-corrosive silicone material that meets the requirements of MIL-A-46146, and will form a cured skin within 60 minutes after exposure to atmospheric moisture without the formation of corrosive by-products. This material will remain flexible and conductive and can be used in environments where temperatures range from -60 to +350° F without degradation of physical or electrical properties. **ECS Conduct-o-Bond 2000** is a thixotropic paste that can be applied to vertical surfaces without sagging. **ECS Conduct-o-Bond 2000** can be used for form-in-place conductive gasketing to attach shielding windows to frames or bezels, bonding conductive elastomer gaskets, and for providing EMI and environmental protection as a sealant.



Ask about other types of conductive adhesives offered by ECS...

Elastomer Adhesive	Silicone
Filler Material:	Nickel Coated Graphite
Color:	Dark Grey



Specific Gravity (+/-0.25)		2.010	ASTM D792
Hardness (Shore A) (+/-7)		65	ASTM D2240
Tensile Strength (PSI)	Min.	500	ASTM D412
Elongation (%)	Min.	100	ASTM D412
	Max.	300	
Peel Strength (PPI)	Min.	4.0	ASTM D1876
Lap Shear (PSI)	Min.	130	ASTM D1002
Upper Operating Temp. (°F)	Max.	+350	
Lower Operating Temp. (°F)	Min.	-60	ASTM D1329
Compression Deflection (%)	Min.	2.5	ASTM D575
Tack Free	Min.	60	
Light Handling	Hrs.	12-24	
Full Cure	Hrs.	96-144	
Volume Resistivity, Ohm/cm	Max.	.100	MIL-DTL-83528 Para. 4.6.11
Shelf Life, From Date Of Shipment In Original Closed Container	Months	6	



7635 RONSON ROAD • SAN DIEGO, CALIFORNIA 92111 • TEL: 858-278-3270 • FAX: 858-278-2950  
E-MAIL: sales@sandiego seal.com • VISIT US AT: www.sandiego seal.com

# Conduct-O-Bond ECS5000

## Technical Data Sheet Conduct-o-Bond ECS5000 Electrically Conductive Adhesive

**Conduct-o-Bond 5000** is a one part, silicone elastomer base, electrically conductive adhesive containing micron sized Silver Plated Aluminum particles as the conducting and shielding media. **ECS Conduct-o-Bond 5000** is a room temperature vulcanizing (RTV) and sealing material that cures in the presence of atmospheric moisture. This adhesive is specially formulated with a high quality non-corrosive silicone material that meets the requirements of MIL-A-46146, and will form a cured skin within 60 minutes after exposure to atmospheric moisture without the formation of corrosive by-products. This material will remain flexible and conductive and can be used in environments where temperatures range from -60 to +350° F without degradation of physical or electrical properties. **ECS Conduct-o-Bond 5000** is a thixotropic paste that can be applied to vertical surfaces without sagging. **ECS Conduct-o-Bond 5000** can be used for form-in-place conductive gasketing to attach shielding windows to frames or bezels, bonding conductive elastomer gaskets, and for providing EMI and environmental protection as a sealant. ECS Conduct-o-Bond 5000 works especially well in harsh environments where corrosion is a concern. Also available with passivated silver aluminum particulars for extra corrosion protection.



Ask about other types of conductive adhesives offered by ECS...

Elastomer Adhesive	Silicone
Filler Material:	Silver Plated Aluminum
Color:	Tan



Specific Gravity (+/-0.25)		1.85	ASTM D792
Hardness (Shore A) (+/-7)		70	ASTM D2240
Tensile Strength (PSI)	Min.	260	ASTM D412
Elongation (%)	Min.	100	ASTM D412
Peel Strength (PPI)	Min.	4.0	ASTM D1876
Lap Shear (PSI)	Min.	175	ASTM D1002
Upper Operating Temp. (°F)	Max.	+350	
Lower Operating Temp (°F)	Min.	-60	ASTM D1329
Compression Deflection (%)	Min.	2.5	ASTM D575
Tack Free	Min.	60	
Light Handling	Hrs.	12-24	
Full Cure	Hrs.	96-144	
Volume Resistivity, Ohm/cm	Max.	.009	MIL-DTL-83528 Para. 4.6.10
Shelf Life, From Date Of Shipment In Original Closed Container	Months	6	

Performance of electrically conductive adhesives vary from one application to another. Cannot guarantee that the above specifications will be met in your application. If you need further assistance in evaluating your application, please do not hesitate to contact ECS for additional information.



7635 RONSON ROAD • SAN DIEGO, CALIFORNIA 92111 • TEL: 858-278-3270 • FAX: 858-278-2950  
E-MAIL: sales@sandiegoseal.com • VISIT US AT: www.sandiegoseal.com